

s 2019 0047

The invention relates to the corrosion protection of metals in water and can be used for corrosion inhibition in closed steel pipeline systems.

The process for corrosion protection of steel in water consists in introducing 50-150 mg/L of calcium borogluconate and 25-300 mg/L of sodium molybdate into the corrosive medium.

The technical result of the invention consists in reducing the corrosion rate of steel in water.

Claims: 1